



Enviro Science Technologies

P.O.

11232, SHAWNEE MISSION, KANSAS 66207-1232
Phone # 913-677-4900 Fax # 913-677-4901 est@everestkc.net

BOX

GYM –FLOOR FINISH HIGH GLOSS- WB

Features

- Single-component formula means no pot life and no mess. Finish is useable the next day if more coats are desired.
- Contains reactive polymers that offer durability and appearance equal or greater than oil-modified products.
- Excellent black mark, scuff and soil resistance.
- One hour dry time between coats under normal conditions.
- Only 24-hour gym down time.
- Uniquely restorable with high-speed buffer.
- Suitable for oak, maple and parquet floors.
- MFMA approved - meets all standards set for group five products
- VOC –compliant
- Slip resistant- UL classified

Technical data

- **Type** - Urethane/Acrylic Blend
- **Form** - Opaque Liquid
- **Odor** - Bland
- **Color** - Light Yellow
- **Weight per Gallon** - 8.60 Lbs.
- **pH** - 7.5-8.5
- **Floor Solids** - 29%
- **Coverage** - Up To 1000 Sq. Ft. Per Gallon (25 m² Per Liter)
- **Slip-Resistance** - UL Classified
- **VOC Content** - 250 gm/L

General Directions*****

- 1. Prepare Floor:** Note: This finish is not designed for application to bare wood floors. Use only on previously sealed surfaces.
Scrub and recoat: Dust mop floor and remove all chewing gum and labels. Clean floor with a 8 ounce per gallon dilution of Citra clean and shine. Use Screen with a 120-grit screen or brown or black pad to sufficiently roughen floor. Rinse the floor with Neutral-7 cleaner until all residues have been removed.
Note: Test previously coated floor in an inconspicuous area before recoating to determine compatibility with existing finish. Apply 2 or 3 coats of finish. See finish application instructions below.
- 2. Apply Finish:** Stir gently before using. Apply at a rate of 800-1000 square feet per gallon. Use a clean, synthetic applicator. Apply thin, even coats with the grain of the wood. Allow a dry time of at least 1 hour between coats. Humid conditions will necessitate longer dry time. After the first coat has dried, apply a second coat. It may be necessary to screen the first coat if grain rising has occurred or it has dried longer than 4 hours. If so, screen the floor with a previously used 120-grit screen or brown or black pad. Always vacuum and tack thoroughly after screening.
Note: Do not pour unused finish back into original container. For best results, use product within 1 year of purchase date.
- 3. Maintain Daily:** Dust mop at least daily, or more as required, to keep floor dust and dirt free. Damp mop spills, salt residue, etc. with neutral-7 Cleaner and a thoroughly wrung mop.
- 4. Maintain Weekly:** If soil conditions are heavy, auto-scrub weekly with red pads and a 2 ounce per gallon dilution of Neutral-7 Cleaner. Refer to the Wood Floor Care Wall Chart or Manual for further details.
- 5. Restoration:** Dust mop floor. Auto-scrub with red pads with an 8-ounce per gallon dilution of Citra clean and Shine. Then dry burnish with recommended pad.

Application Hints

1. GYM FLOOR FINISH-WB should be gently mixed before application.
2. During application, make sure air handlers are OFF and doors are closed to eliminate flash drying. After the application is complete and the finish has skinned over, ventilation can be turned back on.
3. GYM FLOOR FINISH-WB can be applied over most existing finishes including oil-modified products. If uncertain, test in a small, inconspicuous area for compatibility first.
4. Under high humidity, dry times for GYM FLOOR FINISH-WB will vary greatly. Do not apply a second coat if the first coat is still tacky.
5. Two coats are usually sufficient on recoats. If a third coat is desired, make sure the previous coats are thoroughly dry before applying product.